



## Brown Fused Alumina – 95%

FORMULA	Al <sub>2</sub> O <sub>3</sub>		
APPEARANCE	Free flowing abrasive powder/granules		
CHEMICAL ANALYSIS	Al <sub>2</sub> O <sub>3</sub>	95	% min
	TiO <sub>2</sub>	3.0	% max
	Fe <sub>2</sub> O <sub>3</sub>	0.4	% max
	SiO <sub>2</sub>	1.0	% max
SIZING	As per customer's specific requirements, including FEPA grades		
PACKAGING	25 kg bags		

The data given on this sheet is based on test results believed to be representative of the product and should not be interpreted as a binding specification.

Richard Baker Harrison Ltd.  
253 Cranbrook Road  
Ilford, Essex.  
IG1 4TQ  
U.K.



GB94/3715

Tel : +44 (0)20 8554 0102  
Telefax : +44 (0)20 8554 9282  
E-mail : rbhltd@aol.com  
www : rbhltd.com