



Calcined Magnesite 94/200

FORMULA

MgO

APPEARANCE

Free flowing light coloured powder

SPECIFICATION

MgO 94 % min

- 75 microns (200 mesh) 95 % min

TYPICAL PROPERTIES

SiO₂ 1 %

CaO 2 %

R₂O₃ 0.7 %

LOI 2 %

The data given on this sheet is based on test results believed to be representative of the product and should not be interpreted as a binding specification.

Richard Baker Harrison Ltd.
253 Cranbrook Road
Ilford, Essex.
IG1 4TQ
U.K.



GB94/3715

Tel : +44 (0)20 8554 0102
Telefax : +44 (0)20 8554 9282
E-mail : rbhltd@aol.com
www : rbhltd.com