



Dead Burned Magnesite 95%

FORMULA

MgO

APPEARANCE

Free flowing light coloured powder

SPECIFICATION

MgO	95.0 % min
SiO ₂	2.2 % max
CaO	1.6 % max
Fe ₂ O ₃	0.9 % max
Al ₂ O ₃	0.7 % max
LOI	0.5 % max
Bulk Density	3.2 g/cm ³

SIZING

Available in graded and powder forms in accordance with the buyer's requirements

The data given on this sheet is based on test results believed to be representative of the product and should not be interpreted as a binding specification.

Richard Baker Harrison Ltd.
253 Cranbrook Road
Ilford, Essex.
IG1 4TQ
U.K.



GB94/3715

Tel : +44 (0)20 8554 0102
Telefax : +44 (0)20 8554 9282
E-mail : rbhltd@aol.com
www : rbhltd.com