



RICHARD BAKER HARRISON LTD.
INDUSTRIAL MINERALS, COLOURS & CHEMICALS

TECHNICAL DATA SHEET

LITHOPONE 30% RED SEAL B311 GRADE

SPECIFICATION

Total of Zinc and BaSO ₄	99.0% min
Total of Zinc (as ZnS)	30.0% min
Zinc oxide (as ZnO)	0.3% max
Volatile matters at 105°C	0.3% max
Soluble matter in water	0.4% max
Screen residues (63 um mesh)	0.1% max
Colour	Fine white powder
pH value	6 to 8
Oil absorption	10 g/100 g max
Bulk density	0.93 ml/g to 0.98 ml/g

All these figures are given in good faith and should not be interpreted as a binding specification

**253 CRANBROOK ROAD
ILFORD, ESSEX, IG1 4TQ**



GB94/3715

TELEPHONE: +44 (0) 20 8554 0102
FACSIMILE: +44 (0) 20 8554 9282
E-mail: rbhltd@aol.com