



Slate Powder 99/350

APPEARANCE

Grey Powder

SPECIFICATION

350 mesh sieve residue 1.0 % maximum

TYPICAL PROPERTIES

240 mesh sieve residue	0.1 %
300 mesh sieve residue	0.5 %
- 20 microns	85.0 %
- 10 microns	57.0 %
- 5 microns	26.0 %
- 2 microns	6.0 %

CHEMICAL ANALYSIS - XRF

Silica	SiO ₂	55.20 %
Alumina	Al ₂ O ₃	23.52 %
Ferrous oxide	FeO	7.14 %
Ferric oxide	Fe ₂ O ₃	0.66 %
Titania	TiO ₂	0.95 %
Manganese oxide	MnO	0.10 %
Lime	CaO	0.36 %
Magnesia	MgO	2.50 %
Potash	K ₂ O	3.49 %
Soda	Na ₂ O	1.23 %
Phosphoric anhydride	P ₂ O ₅	0.13 %
Water	- 105°C	0.23 %
	+105°C	4.12 %

The data given on this sheet is based on test results believed to be representative of the product and should not be interpreted as a binding specification.

Richard Baker Harrison Ltd.
253 Cranbrook Road
Ilford, Essex.
IG1 4TQ
U.K.



GB94/3715

Tel : +44 (0)20 8554 0102
Telefax : +44 (0)20 8554 9282
E-mail : rbhltd@aol.com
www : rbhltd.com