

| | | |
|---|--|-----------|
| Name | Deostab | |
| Description | vulcanization stabilizer | |
| Composition | cross-linked fatty oils with addition of special stabilizer | |
| Appearance | white ground product | |
| Analytical values | | |
| Ash, 2 h at 950 °C (%) | DIN EN ISO 3451-1 | 5.0 – 7.0 |
| Density at 20°C (g/cm ³) | DIN ISO 787 part 10A | 1.1 |
| Dosage (phr) | 0.5 - 2 | |
| German Food Legislation (BfR recommendation XXI) | approved | |
| Supply Form | 20 kg in PE-bags | |
| Storage Stability | | |
| in originally sealed package in cool and dry places | min. 1 year | |

Application

Cure stabilizer for EPDM compounds containing CaO.
Deostab improves state of cure and compression set without affecting the desiccant action of CaO by reducing the negative influence of CaO in the vulcanization course.

Notes

For detailed description of mechanism, technological effects and dosages see DOG-Kontakt 35.