

Name	Deotack 70 DL	
Description	resinous synthetic plasticizer	
Composition	aromatic polyether, adsorbed on silica	
Active Substance (%)	70 ± 2	
Appearance	white, dust-free powder	
Analytical Values		
Ash, 2 h at 950 °C (%)	DIN EN ISO 3451-1	26.5 - 28.5
Density at 20°C (g/cm ³)	DIN ISO 787 part 10 A	1.3
Dosage (phr)	5 – 25	
German Food Legislation (BgVV recommendation XXI)	approved	
Supply Form	25 kg in cardboard boxes with internal PE-bag	
Storage Stability		
In originally sealed package in cool and dry places	min. 1 year	

Behaviour and Effects

Deotack 70 DL increases building tack of compounds with low own tack. Deotack 70 DL facilitates processing of synthetic rubber compounds, and provides a better dispersion of carbon black and light active fillers.

Application

Deotack 70 DL is mainly used in goods for technical purposes based on synthetic polymers. It is especially suited for oil resistant goods e. g. based on NBR or CR, as it is hardly extracted from vulcanizates by aliphatic hydrocarbons and mineral oils.

Any technical consultation provided by us merely constitutes a guideline without any committal - even with regard to any third party's rights - and will not dispense from the client's examination of the products supplied by us. Processing operations, application and use of our products will be the client's exclusive responsibility. We guarantee the faultless quality of our goods, as defined in our General Terms of Sale and Delivery.