

<b>Name</b>	<b>Hansa F</b>	
<b>Description</b>	white, free-flowing sulphur chloride factice	
<b>Composition</b>	Refined rapeseed oil, cross-linked with sulphur chloride, with inorganic stabilizers, free of mineral oil	
<b>Appearance</b>	ivory ground product	
<b>Analytical values</b>		
Acetone extract (%)	DIN ISO 1407	8 - 10
Ash, 2 h at 950 °C (%)	DIN EN ISO 3451-1	8 - 12
Density at 20°C (g/cm <sup>3</sup> )	DIN ISO 787 part 10A	1.1
Free sulphur (%)	Auler method	max. 0.1
<b>German Food Legislation (BgVV recommendation XXI)</b>	approved	
<b>Supply Form</b>	20 kg in PE-bags	
<b>Storage Stability</b>		
in originally sealed package		
in cool and dry places	min. 1 year	

**Application**

For white and pastel coloured articles based on general purpose rubbers, especially for extruded sections. Hansa factice imparts the best dimensional stability of all factices and has only slight influence on compression set. Vulcanizates containing Hansa factice are less resistant against swelling in water than those containing white sulphur factice.

**Notes**

For detailed description of technological effects and dosages see DOG-Kontakt 38.

Any technical consultation provided by us merely constitutes a guideline without any committal - even with regard to any third party's rights - and will not dispense from the client's examination of the products supplied by us. Processing operations, application and use of our products will be the client's exclusive responsibility. We guarantee the faultless quality of our goods, as defined in our General Terms of Sale and Delivery.