



LINDAU CHEMICALS INC.

COLUMBIA, SOUTH CAROLINA 29201
731 ROSEWOOD DRIVE

PHONE 803-799-6863
TELEFAX 803-256-3639
EMAIL LCI@LINDAU.NET

LINDRIDE 35

SPECIFICATION

		<u>Method</u>
Description	Clear, light amber liquid	Visual
Brookfield Viscosity (cps @ 25°C)	50 – 150	LD Procedure # 7
Gardner Colour	10 maximum	LD Procedure # 5
Anhydride Molecular Weight	165 – 175	LD Procedure # 9
Gel Time (minutes @ 100°C)	30 - 35	LD Procedure # 10C
Volatiles	200 ppm maximum	LD Procedure # 2

TYPICAL PROPERTIES

Specific Gravity @ 25°C	1.19 – 1.22
Weight/gallon @ 25°C	9.90 - 10.15 lbs/gal
Flash Point (TCC)	275°F minimum