



## Liga Aluminium Stearate D2

### APPEARANCE

White Powder

### PROPERTIES

Bulk density	230 ± 50 g/l
Ash content	10.0 – 11.0 %
Loss on drying	2.0 % max
Free fatty acids	3.0 – 5.0 %
Water soluble salts	1.0 % max
Melting point	170 ± 5°C

The data given on this sheet is based on test results believed to be representative of the product and should not be interpreted as a binding specification.

Richard Baker Harrison Ltd.  
253 Cranbrook Road  
Ilford, Essex.  
IG1 4TQ  
U.K.



GB94/3715

Tel : +44 (0)20 8554 0102  
Telefax : +44 (0)20 8554 9282  
E-mail : rbhltd@aol.com  
www : rbhltd.com