



GENICEL™

Product:

Pellet for the production of modified asphalt

Character	Value	Unit
Appearance	• grey pellets	
Fibre	• Approx. 59	%
Bitumen modifier	• Approx. 41	%
Fibre		
∅ Fibre length	• Approx. 1100	µm
∅ Fibre diameter	• Approx. 45	µm
Bitumen modifier		
Congealing point	• min. 99	°C
DIN-ISO 2207		
Needle penetration, 25°C	• max. 1	1/10mm
Needle penetration, 65°C	• max. 10	1/10mm
DIN 51 579		
Viscosity at 135°C	• 10 – 14	mPa x s
DIN 51 562s		

The data given on this sheet is based on test results believed to be representative of the product and should not be interpreted as a binding specification.

Richard Baker Harrison Ltd.
253 Cranbrook Road
Ilford, Essex.
IG1 4TQ
U.K.



GB94/3715

Tel : +44 (0)20 8554 0102
Telefax : +44 (0)20 8554 9282
E-mail : rbhltd@aol.com
www : rbhltd.com