



# TECHNOCEL<sup>®</sup> 1004-5

## Product:

Functional cellulose fibre

Character	Value	Unit
Appearance	• short grey fibre	
Bulk density	• >40	g/l
Loss on drying	• < 7	%
pH-value	• 7-9	
Sieve analysis (Alpine Air Draught Sieve)		
less than 500 µm	• > 95	%
less than 200 µm	• > 70	%
less than 32 µm	• > 5	%

## Application

TECHNOCEL<sup>®</sup> natural fibres are non toxic and physically harmless They are produced from natural resources.

TECHNOCEL<sup>®</sup> can perform as a thixotropic agent. It also reinforces the final structural properties and can be used as a functional filler.

The data given on this sheet is based on test results believed to be representative of the product and should not be interpreted as a binding specification.

Richard Baker Harrison Ltd.  
253 Cranbrook Road  
Ilford, Essex.  
IG1 4TQ  
U.K.



GB94/3715

Tel : +44 (0)20 8554 0102  
Telefax : +44 (0)20 8554 9282  
E-mail : rbhltd@aol.com  
www : rbhltd.com