



Zinc Oxide 99.5 %

APPEARANCE

White Powder

SPECIFICATION

ZnO (Dry basis)	99.5	% minimum
PbO	0.12	% maximum
CdO	0.02	% maximum
CuO	0.006	% maximum
Mn	0.0002	% maximum
HCl Insoluble material	0.02	% maximum
Water insoluble material	0.4	% maximum
325 mesh residue	0.28	% maximum
Moisture content	0.4	% maximum

The data given on this sheet is based on test results believed to be representative of the product and should not be interpreted as a binding specification.

Richard Baker Harrison Ltd.
253 Cranbrook Road
Ilford, Essex.
IG1 4TQ
U.K.



GB94/3715

Tel : +44 (0)20 8554 0102
Telefax : +44 (0)20 8554 9282
E-mail : rbhltd@aol.com
www : rbhltd.com