



## BARYTES B2000

### MINERALOGICAL COMPOSITION

A high purity natural barium sulphate which may contain trace quantities of calcium carbonate and/or silica

Free Quartz 0.5 %

### CHEMICAL ANALYSIS

BaSO<sub>4</sub> 95.00 % min  
 CaCO<sub>3</sub> 0.30 %  
 SiO<sub>2</sub> 1.15 %  
 Fe<sub>2</sub>O<sub>3</sub> 0.04 %  
 Al<sub>2</sub>O<sub>3</sub> 0.13 %

### CHEMICAL PROPERTIES

Loss on ignition 0.07 %  
 Solubility in water 0.09 %  
 Acid soluble barium 100 ppm max  
 pH 7

### PHYSICAL PROPERTIES


Specific gravity 4400 kg/m<sup>3</sup>  
 Tamped density 1900 kg/m<sup>3</sup>  
 Hardness (Mohs) 3  
 Oil absorption 12 g/100g

Whiteness Minolta Cr 200 L\* 92.9  
 a\* 0.3  
 b\* 5.2  
 Y 82.8  
 L\* 90 min

% passing 53 micron sieve 99.99 % min  
 % passing 45 micron sieve 99.99 % min

#### Particle size distribution - Malvern 3601

- 75 um 100 %  
 - 30 um 100 %  
 - 20 um 99 %  
 - 10 um 89 %  
 Average particle size d<sub>50</sub> 5.0 microns



### PACKAGING

Dry powder in 25 kg paper bags 0.3 % moisture content max

The data given on this sheet is based on test results believed to be representative of the product and should not be interpreted as a binding specification.

Richard Baker Harrison Ltd.  
 Marsh Trees House, Marsh Parade  
 Newcastle under Lyme  
 ST5 1BT  
 U.K.



GB94/3715

Tel : +44 (0)1782 622666  
 Telefax : +44 (0)1782 622655  
 E-mail : sales@rbhltd.com  
 www : rbhltd.com