



18.04.2006

Calcined Magnesite [Low Lime]

FORMULA

MgO

APPEARANCE

Free flowing light coloured powder

SPECIFICATION

MgO	94 % min
120 mesh passing	95 % min
SiO ₂	2 % max
CaO	1.2 % max
R ₂ O ₃	1.0 % max
Fe ₂ O ₃	0.7 % max
Chlorides	200 ppm max
LOI	1.2 % max

The data given on this sheet is based on test results believed to be representative of the product and should not be interpreted as a binding specification.

Richard Baker Harrison Ltd.
253 Cranbrook Road
Ilford, Essex.
IG1 4TQ
U.K.



GB94/3715

Tel : +44 (0)20 8554 0102
Telefax : +44 (0)20 8554 9282
E-mail : rbhltd@aol.com
www : rbhltd.com