

MICA MKT™

IMERYS PERFORMANCE & FILTRATION MINERALS

IMERYS Ceramics France
Kaolins de Bretagne
Lanvrian - 56276
Ploemeur Cedex - France
Tel: +33 2 97 86 16 16
Fax: +33 2 97 86 16 11

IMERYS Minerals Ltd
Par Moor Centre,
Par Moor Road, Par
Cornwall, England
PL24 2SQ
Tel: +44 1726 818000
Fax: +44 1726 811200

SPECIFICATION


Moisture	(mass % max.)	1.0
L.O.I	(mass %)	5.7±1.0
+ 90 µm	(mass % max.)	0.1
- 20 µm	(mass % min.)	96
- 2 µm	(mass % max.)	35

TYPICAL PROPERTIES

SiO ₂	(mass %)	64
Al ₂ O ₃	(mass %)	24
K ₂ O	(mass %)	4.5
Fe ₂ O ₃	(mass %)	0.8
Brightness	(ISO - R457)	77
Yellowness		6.5
Aerated powder density	(g/l)	300



TYPICAL PARTICLE SIZE DISTRIBUTION GRAPH



The data quoted are determined by the use of IMERYS Minerals Ltd Standard Test Methods, copies of which will be supplied on request. Every precaution is taken to ensure the products conform to our published data, but since the products are based on naturally occurring raw materials, we reserve the right to change these data should it become necessary. Sales are in accordance with our 'Conditions of Sale', copies of which will be supplied on request.