

MICA-MU™ 454

IMERYS PERFORMANCE & FILTRATION MINERALS

IMERYS Ceramics France

Kaolins de Bretagne
Lanvrian - 56276
Ploemeur Cedex - France
Tel: +33 2 97 86 16 16
Fax: +33 2 97 86 16 11

IMERYS

Par Moor Centre,
Par Moor Road, Par
Cornwall, England
PL24 2SQ
Tel: +44 1726 818000
Fax: +44 1726 811200

TYPICAL PROPERTIES

+ 50 µm	(mass %)	94
+ 150 µm	(mass %)	49
+ 315 µm	(mass %)	5
+ 400 µm	(mass %)	1 ± 1
Moisture	(mass %)	0.5
Surface area	(BET, m ² /g)	1.5
Aerated powder density	(kg/m ³)	700

Chemical Analysis (mass %)

SiO ₂	51
Al ₂ O ₃	32
K ₂ O	8.5
MgO	0.6
Fe ₂ O ₃	2.0
L.O.I.	5.4 ± 0.8



The data quoted are determined by the use of IMERYS Minerals Ltd Standard Test Methods, copies of which will be supplied on request. Every precaution is taken to ensure the products conform to our published data, but since the products are based on naturally occurring raw materials, we reserve the right to change these data should it become necessary. Sales are in accordance with our 'Conditions of Sale', copies of which will be supplied on request.