



## Ground Silica SL35/200

**PARTICLE SIZE Cumulative Retention**  
**Alpine Jet Sieve Typical % Limit %**  
 75 Microns (BS 200 Mesh) 35.0 32.0 – 37.0

### CHEMICAL ANALYSIS

SiO <sub>2</sub>	99.1%
TiO <sub>2</sub>	0.15%
Al <sub>2</sub> O <sub>3</sub>	0.41%
Fe <sub>2</sub> O <sub>3</sub>	0.06%
CaO	0.03%
MgO	0.02%
K <sub>2</sub> O	0.10%
Na <sub>2</sub> O	0.03%

### PHYSICAL PROPERTIES

Loss on Ignition 0.19

<b>PARTICLE SIZE</b>	<b>Cumulative Retention</b>	
	<b>Typical %</b>	<b>Limit %</b>
<b>Alpine Jet Sieve</b>		
75 Microns (BS 200 Mesh)	35.0	32.0 – 37.0

The data given on this sheet is based on test results believed to be representative of the product and should not be interpreted as a binding specification

Richard Baker Harrison Ltd.  
 Marsh Trees House, Marsh Parade  
 Newcastle Under Lyme  
 ST5 1BT  
 U.K.



GB94/3715

Tel : +44 (0)1782 622666  
 Fax : +44 (0)1782 622655  
 E-mail : sales@rbhltd.com  
 www : rbhltd.com