

Hyplas™ 71



Hyplas™
is a trade mark of
IMERYS Minerals Ltd

ECC is a business name of
IMERYS Minerals Ltd

The data quoted are determined by the use of standard test methods, copies of which will be supplied on request. Every precaution is taken in production to ensure the products conform to our published data. Since the products are based on naturally occurring materials, we reserve the right to change these data should it become necessary. Sales are in accordance with our "Conditions of Sale", copies of which will be supplied on request.

PRODUCT SPECIFICATION

Chemical Composition (mass %)

	Value	Range	
		Min	Max
SiO ₂	71	68	73
Al ₂ O ₃	18,5	16,5	21
Fe ₂ O ₃	0,8	0,6	1
TiO ₂	1,6	1,4	1,8
K ₂ O	1,9	1,4	2,2
Loss on ignition	5,3	4,7	5,8

Surface Area - BET (M²/g)

19	14	24
----	----	----

TYPICAL DATA

The following data is provided for information only and is derived from quality control tests over a number of years. It does not constitute a specification.

Chemical Composition (mass %)

CaO	0,1
MgO	0,3
Na ₂ O	0,3
Carbon	0,2

Particle Size (mass %)

5 microns	72
2 microns	58
1 micron	48
0,5 micron	39

Residue (%)

>125	0,7
------	-----

Modulus of Rupture (MNm⁻²)

Dried at 110°C	7,0
----------------	-----

Fired Properties (@ 1170°C)

Water absorption (mass%)	5
--------------------------	---

Brightness (%)	48
----------------	----

Contraction (%)	4,8
-----------------	-----

C1/318/B

November 2008

Hyplas 71

© IMERYS

Sixth Edition.

This supersedes the document dated March 2008



ISO 9001
FM 14752

IMERYS Minerals Ltd
Par Moor Centre
Par Moor Road
Par, Cornwall
PL24 2SQ, UK
Tel: +44 (0) 1726 81 8000
Fax: +44 (0) 1726 81 1200

