

Kaolin Natural BP and Light Kaolin BP

For the Pharmaceutical Industry

KAOLIN NATURAL BP and LIGHT KAOLIN BP are refined natural aluminium silicates freed from most of their impurities by elutriation and drying, LIGHT KAOLIN BP contains a suitable dispersing agent.

These Kaolins conform to the physical and chemical purity required by the British Pharmacopoeia Standard as determined by the test methods defined in that specification and which is date re-issued from time to time.

As supplied these products are not sterile.

SPECIFICATION

Arsenic	2 ppm max
Heavy Metals	20 ppm max
Chloride	330 ppm max
Soluble Matter	10 mg max
Coarse Particles	25 mg max
Fine Particles	70 wt % min
Loss on Drying	1.5 wt % max
Loss on Ignition	15 wt % max

CAS No: 1332-58-7

The data quoted are determined by use of Imerys Standard Test Methods, copies of which will be supplied upon request. Where maximum/minimum limits are indicated, this constitutes a specification. Where no maximum/minimum limits are given the data quoted are typical only. Every precaution is taken in production to ensure the clays conform to our published data, however, as the products are based on naturally occurring raw materials, Imerys Minerals Australia reserves the right to change these data should it become necessary. Unless stamped 'Controlled' in red ink, the reader should check that the data contained herein is current.



Manufactured under a quality system certified as complying with ISO 9001 by an accredited certification body.



Imerys Minerals Australia Pty Ltd
3610 Glenelg Highway Pittong Victoria 3360 Australia
Telephone (03) 5344 7205 Facsimile (03) 5344 7308
Email: rob.hill@imerys.com