



Calcined Magnesite 92/200

FORMULA	MgO	
APPEARANCE	Free flowing light coloured powder	
SPECIFICATION	MgO	91.5 % min
	- 75 microns (200 mesh)	95 % min
TYPICAL PROPERTIES		
	SiO ₂	2.0 %
	CaO	1.6 %
	R ₂ O ₃	1.0 %
	LOI	4.0 %

The data given on this sheet is based on test results believed to be representative of the product and should not be interpreted as a binding specification

RICHARD BAKER HARRISON LTD
 Marsh Trees House, Marsh Parade
 Newcastle under Lyme,
 Staffordshire. ST5 1BT U.K.



Tel: +44 (0) 1782 622666
 Fax: +44 (0) 1782 622655
 E:mail: sales@rbhltd.com
 Web: www.rbhltd.com