

BLUESILTM

RTV 3440, 3445, 3450, 3450 QC A&B

Filler Enforced Elastomers for Moulding and Prototyping

Description

BLUESIL RTV 3440, 3445, 3450, 3450 QC A&B are two component silicone elastomers that crosslink at room temperature by polyaddition reaction. The polymerisation can be accelerated by heat.

The silicone materials are delivered as two viscous liquid components, which once mixed and cured, transform into an elastic and resistant elastomer. Polymerisation occurs without production of heat.

Examples of applications

Reproduction of various kinds of 3D objects in:

- Plaster
- Wax
- Polyester
- Low melting point metals

Advantages

- Highly accurate reproductions
- Dimensional stability
- Good mechanical properties combined with a high Shore A
- Chemical and thermal resistance
- Fast mixing and easy processing due to the low viscosity

Characteristics

1. Characteristics of the non cured product

Properties	RTV 3440		RTV 3445		RTV 3450		RTV 3450 QC	
	A	B	A	B	A	B	A	QC B
Contains:	Pt	SiH	Pt	SiH	Pt	SiH	Pt	SiH
Appearance	A: viscous liquid				B: low viscous liquid			
Colour	beige	blue	beige	blue	beige	black / translucent	beige	black / translucent
Density [g/cm ³] at 23 °C, approx.	1.3	1.1	1.3	1.1	1.3	1.1	1.3	1.1
Viscosity [mPa·s] at 23 °C, approx	40000	500	40000	200	40000	200	45000	500

BLUESIL™ RTV 3440, 3445, 3450, 3450 QC A&B**Characteristics (cont')****2. Polymerisation**

Properties	RTV 3440 A&B	RTV 3445 A&B	RTV 3450 A&B	RTV 3450 QC A&B
Mixing Ratio A : B <i>parts by weight</i>	10 : 1	10 : 1	10 : 1	10 : 1
Working Time <i>[min] at 23 °C, approx.</i>	90	60	90	20
Demoulding Time <i>h] at 23 °C, approx.[</i>	24	24	16	4
Mixing viscosity <i>[mPa·s] at 23 °C, approx.</i>	15000	13000	15000	15000

3. Characteristics of the cured product

	RTV 3440 A&B	RTV 3445 A&B	RTV 3450 A&B	RTV 3450 QC A&B
Hardness Shore A <i>approx. DIN 53 505</i>	40	45	50	50
Tensile strength <i>[N/mm²] approx. DIN 53 504 specimen S3A</i>	4	4	5	5
Elongation <i>[%] approx. DIN 53 504 specimen S3A</i>	300	300	300	300
Tear strength <i>[N/mm] approx. DIN 53 515</i>	9	10	8	8

Remarks:

Curing the silicone at elevated temperature has no influence on the final properties of **BLUESIL RTV 3440, 3445, 3450 and 3450 QC A&B**. Nevertheless, heating can alter the dimensions.

Processing**1. Mixing the two components**

BLUESIL RTV 3440, 3445, 3450, 3450 QC A&B are mixed by weight in the above indicated ratio. The mixing can be carried out either by hand or using a low-speed electric or pneumatic mixer to minimise the introduction of air and to avoid any temperature increase.

It is also possible to use a special mixing and dispensing machine for the two silicone components. Further information is available upon request.

2. Degassing

The mixture should be degassed preferably at 30 to 50 mbar to eliminate any entrapped air. If a dispensing machine is used, the two components are degassed separately prior to mixing.

The silicone mixture expands to 3 to 4 times of its initial volume and bubbles rise to the surface.

The bubbles progressively disappear and the mixture returns to its initial volume after 5 to 10 minutes. Wait a few minutes to complete the degassing and then flash the vacuum. The silicone is ready for pouring, either by gravity or under low pressure.

Note: Flashing the vacuum once or twice accelerates the degassing. It is recommended to use a container with a high diameter / height ratio.

BLUESIL™ RTV 3440, 3445, 3450, 3450 QC A&B

Processing (cont')

3. Polymerisation

BLUESIL RTV 3440, 3445, 3450, 3450 QC A&B polymerises at 23 °C. The curing may be slowed down at lower temperature and contrary accelerated by heat.

Contact with certain materials can inhibit the crosslinking. See list below:

- natural rubbers vulcanised with sulphur,
- RTV 2 silicone elastomers catalysed with metal salts, e.g. tin-compounds,
- PVC stabilised with tin salts and additives,
- epoxy resins catalysed with amines,
- some organic solvents, e.g. ketones, alcohols, ether etc.

In case of doubts, it is recommended to test the substrate by applying a small quantity of the mixed silicone on a restricted area.

Packaging

BLUESIL RTV 3440, 3450, 3450 QC A&B are delivered in pails of 25 kg for A component and 2,5 kg for B component.

BLUESIL RTV 3445 A&B is delivered in pails of 20 kg for A component and 2 kg for B component.

BLUESIL RTV 3450 is also delivered in drums of 200 Kg for A component and in pails of 20 Kg for B part.

Storage and shelf life

When stored in its original unopened packaging, at a temperature of between -10°C and +30°C, **BLUESIL RTV 3440, 3445, 3450, 3450 QC A&B** may be stored for up to 12 months from the date of manufacture clearly marked on the packaging.

Beyond this date, Bluestar Silicones no longer guarantees that the product meets the sales specifications.

Safety

Please consult the Safety Data Sheets of **BLUESIL RTV 3440, 3445, 3450** and **3450 QC A&B**.

Visit our website www.bluestarsilicones.com

EUROPE

Bluestar Silicones France
21 Avenue Georges Pompidou
F69486 Lyon Cedex 03
FRANCE
Tel. (33) 4 72 13 19 00
Fax (33) 4 72 13 19 88

NORTH AMERICA

Bluestar Silicones USA
2 Tower Center Boulevard
Suite 1601
East Brunswick, NJ 08816-1100
United States
Tel. (1) 732 227-2060
Fax. (1) 732 249-7000

LATIN AMERICA

Bluestar Silicones Brazil Ltda.
Av. Maria Coelho Aguiar, 215
Bloco G – 1º andar
05804-902-Sao Paulo – SP-
Brazil
Tel. (55) 11 37477887

ASIA PACIFIC

Bluestar Silicones Hong Kong
Trading Co. Ltd
29th Floor, 88 Hing Fat Street
Causeway Bay
Hong Kong
Tel. (852) 3106 8200
Fax (852) 2979 0241

Warning to the users

The information contained in this document is given in good faith based on our current knowledge. It is only an indication and is in no way binding, particularly as regards infringement of or prejudice to third party rights through the use of our products. BLUESTAR SILICONES guarantees that its products comply with its sales specifications. This information must on no account be used as a substitute for necessary prior tests which alone can ensure that a product is suitable for given use. Users are responsible for ensuring compliance with local legislation and for obtaining the necessary certifications and authorisations. Users are requested to check that they are in possession of the latest version of this document and BLUESTAR SILICONES is at their disposal to supply any additional information.