

BLUESILTM PRIM PM 811 A & B – PRIM PM 812 A & B

Polyaddition Primers for Silicone Adhesion

Description	BLUESIL PRIM PM 811 A&B and BLUESIL PRIM PM 812 A&B are two component bonding agents to improve the adhesion of silicones to various substrates in combination with BLUESIL PRIM PM 820 (UVT). The primers are supplied as low viscous solutions of the active ingredients.
Examples of applications	Adhering Pt catalysed silicones onto various substrates such as: <ul style="list-style-type: none"> Aluminium and other metals Reinforced epoxy resins, polyurethane and other polymers
Advantages	<ul style="list-style-type: none"> Quick processing due to high volatility Highest performance adhesion in combination with BLUESIL PRIM PM 820 (UVT).

Characteristics

Properties	BLUESIL PRIM PM 811		BLUESIL PRIM PM 812	
	A	B	A	B
Contains	Pt catalyst	SiH crosslinker	Pt catalyst	SiH crosslinker
Appearance	Low viscous liquid	Low viscous liquid	Low viscous liquid	Low viscous liquid
Colour	Translucent	Transparent	Translucent	Transparent
Density [g/cm ³] at 23 °C, approx.	0.77	0.68	0.77	0.71
Viscosity [mPa·s] at 23 °C, approx	1	1	1	1
Mixing Ratio A : B parts by weight	10 : 1		10 : 1	
Pot life [mPa·s] at 23 °C, approx	> 3 days		> 3 hours	
Non-volatile content [wt.-%] ,approx	25	8	25	12
Boiling point [°C], approx	100	60	100	100
Solvent	Aliphatic hydrocarbon			

BLUESIL™ PRIM PM 811 A & B – PRIM PM 812 A & B**Processing****1. Working conditions**

Primers are highly flammable liquids! Ensure to work in a well-ventilated work space free of any source of ignition.

The working temperature should range between 5°C and 30 °C. Higher temperatures will cause a very fast evaporation and thus lead to irregular layers of the primer.

In order to avoid premature reaction of the primer it is recommended to fill only small amounts into a small beaker and re-seal the bottle immediately.

2. Preparation of the substrate

The substrate must be clean, dry and free from grease. It is recommended to clean the surface with acetone. Roughening or structuring the surface will improve the adhesion.

3. Application of primers

All primer components have to be stirred thoroughly before using.

The primers should be applied as a very thin film using a soft brush or a lint-free cloth. A coat weight of 30 – 60 g/m² is recommended depending on the roughness and absorbency of the ground.

In a first step a thin coating of BLUESIL PRIM PM 820 (UVT) has to be applied by brushing or spraying. The film should dry for about 30 min at 23°C.

The components of **BLUESIL PRIM PM 811** and **BLUESIL PRIM PM 812** are mixed in a ratio of A : B = 10 : 1.

A thin coating of the mixture is brushed on the surface. The film should dry again for at least 30 min at 23 °C.

4. Application of the adherent

Apply the silicone elastomer mixture soon after the primer treatment and vulcanise it as recommended in the respective Technical Data Sheets.

Packaging

BLUESIL PRIM PM 811 A and **BLUESIL PRIM PM 812 A** are delivered in bottles of 0.60 kg (1 L).

BLUESIL PRIM PM 811 B and **BLUESIL PRIM PM 812 B** are delivered in bottles of 0.06 kg (0.1 L).

Storage and shelf life

When stored in their original unopened packaging, at a temperature of between -10°C and +30°C, **BLUESIL PRIM PM 811 A&B** and **BLUESIL PRIM PM 812 A&B** may be stored for up to 12 months from the date of manufacture clearly marked on the packaging.

Beyond this date, Bluestar Silicones no longer guarantees that the products meet the sales specifications.

Safety

Please consult the Safety Data Sheets of **BLUESIL PRIM PM 811 A&B** and **BLUESIL PRIM PM 812 A&B**.

BLUESIL™ PRIM PM 811 A & B – PRIM PM 812 A & B

Visit our website www.bluestarsilicones.com

EUROPE

Bluestar Silicones France
21 Avenue Georges Pompidou
F69486 Lyon Cedex 03
FRANCE
Tel. (33) 4 72 13 19 00
Fax (33) 4 72 13 19 88

NORTH AMERICA

Bluestar Silicones USA
2 Tower Center Boulevard
Suite 1601
East Brunswick, NJ 08816-1100
United States
Tel. (1) 732 227-2060
Fax. (1) 732 249-7000

LATIN AMERICA

Bluestar Silicones Brazil Ltda.
Av. Maria Coelho Aguiar, 215
Bloco G – 1º andar
05804-902-Sao Paulo – SP-
Brazil
Tel. (55) 11 37477887

ASIA PACIFIC

Bluestar Silicones Hong Kong
Trading Co. Ltd
29th Floor, 88 Hing Fat Street
Causeway Bay
Hong Kong
Tel. (852) 3106 8200
Fax (852) 2979 0241

Warning to the users

The information contained in this document is given in good faith based on our current knowledge. It is only an indication and is in no way binding, particularly as regards infringement of or prejudice to third party rights through the use of our products. BLUESTAR SILICONES guarantees that its products comply with its sales specifications. This information must on no account be used as a substitute for necessary prior tests which alone can ensure that a product is suitable for given use. Users are responsible for ensuring compliance with local legislation and for obtaining the necessary certifications and authorisations. Users are requested to check that they are in possession of the latest version of this document and BLUESTAR SILICONES is at their disposal to supply any additional information.